

RTM C90 Type One

RTM C90 Type One

BASED ON LEGENDARY SM900 FORMULA


WIDTH: 3.81MM

MINIMAL PRINT-THROUGH

TYPE ONE, NORMAL BIAS

PRODUCED FROM 2020 ONWARDS

MADE IN FRANCE





RTM C90 Type One

Technical Data

	Parameters	Fox C90 Data	Notes
General Properties	C-0 shell	Clear, 5 screws	Tab in
	Maximum recording time	90 min	
	Tape width	3.81 mm (+0.00/-0.05)	
	Tape length	130.9m	
Physical Properties	Coating thickness	5 µm ± 0.5 µm	
	Base film thickness	8 µm ± 0.5 µm	Polyester
	Total Thickness	13 ± 1 µm	
	Yield Strength (3%)	≥ 5 N	
	Breaking Strength	≥ 9 N	
	Electrical resistance of magnetic coating	≤ 4 GΩ	
Magnetic Properties	Coercivity	370 Oe	Ferric Oxide (Fe2O3)
	Saturation retentivity	1500 G	
Electrical properties	Sensitivity at 315Hz	-0.6 dB	Compared to IEC I tape
	Sensitivity at 10kHz	+0.5 dB	Compared to IEC I tape
	Maximum output level at 315Hz (MOL)	+2.2 dB	dB above reference level of 250 nWb/m
	Saturated output level at 10kHz (SOL)	-6 dB	Relative to reference level
	Bias noise	+0.6 dB	Compared to IEC I tape
	Audio S/N ratio	More than 48 dB	

All data given in the specification are subject to change without prior notice due to technical progress

RTM C90 Type One



53 rue Division Leclerc
50300 Avranches
www.recordingthemasters.com